



Surlyn® 1652SB

DuPont Packaging & Industrial Polymers - Ionomer

Monday, September 21, 2020

General Information

Product Description

DuPont™ Surlyn® 1652SB is an ionomer of ethylene acid copolymer.

The resin can be processed in conventional extrusion coating, blown film, cast film, sheet extrusion and coextrusion equipment designed to process polyethylene and ethylene copolymer type resins.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Additive	• Antiblock	• Slip	
Features	• Antiblocking	• Slip	
Uses	• Blown Film • Cast Film	• Film • Sheet	
Agency Ratings	• FDA 21 CFR 177.1330(a)		
Forms	• Pellets		
Processing Method	• Blown Film • Cast Film	• Coextrusion • Sheet Extrusion	

ASTM & ISO Properties¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.942		ASTM D792
Density	0.940	g/cm ³	ISO 1183
Melt Mass-Flow Rate (190°C/2.16 kg)	4.6	g/10 min	ASTM D1238
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	4.6	g/10 min	ISO 1133
Ion Type	Zinc		
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	174	°F	ASTM D1525
Vicat Softening Temperature	174	°F	ISO 306
Peak Melting Temperature	214	°F	ASTM D3417
Melting Temperature (DSC)	214	°F	ISO 3146
Freezing Point			
--	178	°F	ASTM D3417
--	178	°F	ISO 3146

Processing Information

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	320	°F
Cylinder Zone 2 Temp.	410	°F
Cylinder Zone 3 Temp.	455	°F
Cylinder Zone 4 Temp.	455	°F
Cylinder Zone 5 Temp.	455	°F
Adapter Temperature	455	°F
Melt Temperature	365 to 545	°F
Die Temperature	455	°F

Surlyn® 1652SB

DuPont Packaging & Industrial Polymers - Ionomer

Extrusion Notes

Blown Film Processing Parameters:

Feed Temperature: 135°C

Second Zone Temperature: 160°C

Third Zone Temperature: 185°C

Fourth Zone Temperature: 185°C

Fifth Zone Temperature: 185°C

Adapter Temperature: 185°C

Die Temperature: 185°C

Extrusion Coating/Laminating Processing Parameters:

Feed Temperature: 160°C

Second Zone Temperature: 210°C

Third Zone Temperature: 260°C

Fourth Zone Temperature: 285°C

Fifth Zone Temperature: 285°C

Adapter Temperature: 285°C

Die Temperature: 285°C

Notes

¹ Typical properties: these are not to be construed as specifications.