



## Surlyn® 1652SR

DuPont Packaging & Industrial Polymers - Ionomer

Monday, September 21, 2020

### General Information

#### Product Description

DuPont™ Surlyn® 1652SR is an ionomer of ethylene acid copolymer.

The resin can be processed in conventional extrusion coating, blown film, cast film, sheet extrusion and coextrusion equipment designed to process polyethylene and ethylene copolymer type resins.

#### General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Additive	• Chill Roll Release	• Slip	
Features	• Slip		
Uses	• Blown Film • Cast Film	• Coating Applications • Film	• Sheet
Agency Ratings	• FDA 21 CFR 177.1330(a)		
Forms	• Pellets		
Processing Method	• Blown Film • Cast Film	• Coextrusion • Extrusion Coating	• Sheet Extrusion

### ASTM & ISO Properties<sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.942		ASTM D792
Density	0.940	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (190°C/2.16 kg)	5.4	g/10 min	ASTM D1238
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	5.4	g/10 min	ISO 1133
Ion Type	Zinc		
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	174	°F	ASTM D1525
Vicat Softening Temperature	174	°F	ISO 306
Peak Melting Temperature	212	°F	ASTM D3417
Melting Temperature (DSC)	212	°F	ISO 3146
Freezing Point			
--	178	°F	ASTM D3417
--	178	°F	ISO 3146

### Processing Information

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	275	°F
Cylinder Zone 2 Temp.	320	°F
Cylinder Zone 3 Temp.	365	°F
Cylinder Zone 4 Temp.	365	°F
Cylinder Zone 5 Temp.	365	°F
Adapter Temperature	365	°F
Melt Temperature	365 to 545	°F
Die Temperature	365	°F

# Surlyn® 1652SR

## DuPont Packaging & Industrial Polymers - Ionomer

---

### Extrusion Notes

---

The above processing values are for blown film.

Cast film parameters:

- Feed Zone: 160°C
- Second Zone: 210°C
- Third Zone: 235°C
- Fourth Zone: 235°C
- Fifth Zone: 235°C
- Adapter Zone: 235°C
- Die Zone: 235°C

Extrusion coating/lamination parameters:

- Feed Zone: 160°C
- Second Zone: 210°C
- Third Zone: 260°C
- Fourth Zone: 285°C
- Fifth Zone: 285°C
- Adapter Zone: 285°C
- Die Zone: 285°C

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.