



Surlyn® 1705-1

DuPont Packaging & Industrial Polymers - Ionomer

Monday, September 21, 2020

General Information

Product Description

DuPont™ Surlyn® 1705-1 is an ionomer of ethylene acid copolymer.

The resin can be processed in conventional extrusion coating, blown film, cast film, sheet extrusion and coextrusion equipment designed to process polyethylene and ethylene copolymer type resins.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Uses	• Blown Film • Cast Film	• Coating Applications • Film	• Sheet
Agency Ratings	• FDA 21 CFR 177.1330(a)		
Forms	• Pellets		
Processing Method	• Blown Film • Cast Film	• Coextrusion • Extrusion Coating	• Sheet Extrusion

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.952		ASTM D792
Density	0.950	g/cm ³	ISO 1183
Melt Mass-Flow Rate (190°C/2.16 kg)	5.5	g/10 min	ASTM D1238
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	5.5	g/10 min	ISO 1133
Ion Type	Zinc		
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	149	°F	ASTM D1525
Vicat Softening Temperature	149	°F	ISO 306
Peak Melting Temperature	203	°F	ASTM D3417
Melting Temperature (DSC)	203	°F	ISO 3146
Freezing Point			
--	142	°F	ASTM D3417
--	142	°F	ISO 3146

Processing Information

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	275	°F
Cylinder Zone 2 Temp.	365	°F
Cylinder Zone 3 Temp.	410	°F
Cylinder Zone 4 Temp.	410	°F
Cylinder Zone 5 Temp.	410	°F
Adapter Temperature	410	°F
Melt Temperature	320 to 455	°F
Die Temperature	410	°F

Surlyn® 1705-1

DuPont Packaging & Industrial Polymers - Ionomer

Extrusion Notes

Blown Film Processing Parameters:

Feed Temperature: 110°C

Second Zone Temperature: 135°C

Third Zone Temperature: 160°C

Fourth Zone Temperature: 160°C

Fifth Zone Temperature: 160°C

Adapter Temperature: 160°C

Die Temperature: 160°C

Extrusion Coating/Laminating Processing Parameters:

Feed Temperature: 160°C

Second Zone Temperature: 210°C

Third Zone Temperature: 235°C

Fourth Zone Temperature: 235°C

Fifth Zone Temperature: 235°C

Adapter Temperature: 235°C

Die Temperature: 235°C

Notes

¹ Typical properties: these are not to be construed as specifications.